

CBG FireBarrier - 2,5

TDS-No. 7060

Ultra thin, light and universal composite panel on basalt- and glass-ceramic base with endothermic effect.

- 100% natural and chemically neutral
- Antibacterial
- Corrosion-resistant
- Thermoresistant
- Moisture-resistant
- Vibration damping
- Non-combustible
- Non-smouldering
- Recyclable



Properties	Data
Description	Fire protection panel.
Application areas	E.g. fire barriers, connections.
Basis weight, [kg/m ²]:	2,9 ± 0,5.
Total thickness, [mm]:	2,5 ± 0,2.
Material	Ceramic basalt fibre laminates, glass laminate, inorganic fire protection adhesive.
Melting point	≥ 1300°C.
Storage*	Dry, protect from moisture, storage temperature 15 - 30°C.
Shelf life*	3-6 months at room temperature, packed in protective foil.
Safety Instructions*	When processing the above product, the guidelines issued by the chemical industry and the employers' liability insurance association in conjunction with the safety data sheets must be observed.
Processing note*	Only after 24h conditioning to the processing temperature.
General remark*	The above data and information are based on tests and Investigations carried out and are information for the user. Users must confirm and ensure the suitability of this product for the intended purpose by carrying out their own investigations and tests.
Width * / Length *	Up to 1200 ± 1 mm / up to 2980 ± 2 mm.

Delivery

* Various sizes and surfaces are possible on request.

- Delivery on pallets wrapped with stretch film.



Processing and storage

- The usual protective measures must be taken during processing. Gloves, breathing protection and safety glasses are recommended;
- Storage horizontal, e.g. on pallets, on a level surface, secured against slipping.



Subject to modifications

CBG Composites GmbH Egerpohl 2 D-51688 Wipperfürth / Germany
Tel: +49 2267 67 0 / Fax: +49 2267 67 222 / www.cbg-composites.de / info@cbg-composites.de

The technical information on our products reflects the state of our knowledge at the time of printing. Therefore, the latest edition of the data sheet should always be used, as our experience and knowledge are constantly evolving. In case of doubt please contact us. The application shown is only exemplary and may vary in individual cases. It is therefore not relevant for liability. Our general terms and conditions apply, which can also be found on our homepage.